

Integrity All Ultrex	LoE ² -272®			LoE ³ -366®	
	U Factor	SHGC	VLT	Energy Star	Qualifies for Tax Credit
All Ultrex Single Hung - 3 mm glass					
Insulating LoE ² -272 Glass - Argon	0.31	0.33	0.57	N, NC, SC, S	
Insulating LoE ² -272 Glass - Argon, GBG	0.32	0.30	0.51	N, NC, SC, S	
Insulating LoE ³ - 366 Glass - Argon	0.30	0.22	0.51	N, NC, SC, S	X
Insulating LoE ³ - 366 Glass - Argon, GBG	0.30	0.20	0.46	N, NC, SC, S	X

All Ultrex Double Hung - 3 mm glass					
Insulating LoE ² -272 Glass - Argon	0.32	0.33	0.57	N, NC, SC, S	
Insulating LoE ² -272 Glass - Argon, GBG	0.33	0.30	0.51	N, NC, SC, S	
Insulating LoE ³ - 366 Glass - Argon	0.30	0.22	0.51	N, NC, SC, S	X
Insulating LoE ³ - 366 Glass - Argon, GBG	0.30	0.20	0.46	N, NC, SC, S	X

All Ultrex Glider - 3 mm glass					
Insulating LoE ² -272 Glass - Argon	0.31	0.33	0.57	N, NC, SC, S	
Insulating LoE ² -272 Glass - Argon, GBG	0.32	0.30	0.51	N, NC, SC, S	
Insulating LoE ³ - 366 Glass - Argon	0.30	0.20	0.51	N, NC, SC, S	X
Insulating LoE ³ - 366 Glass - Argon, GBG	0.30	0.20	0.46	N, NC, SC, S	X

All Ultrex Sliding Window Picture/Transom - 3 mm glass					
Insulating LoE ² -272 Glass - Argon	0.29	0.34	0.59	N, NC, SC, S	
Insulating LoE ² -272 Glass - Argon, GBG	0.30	0.31	0.53	N, NC, SC, S	
Insulating LoE ³ - 366 Glass - Argon	0.28	0.23	0.53	N, NC, SC, S	X
Insulating LoE ³ - 366 Glass - Argon, GBG	0.29	0.21	0.48	N, NC, SC, S	X

All Ultrex Direct Glaze Polygon - 3 mm glass					
Insulating LoE ² -272 Glass - Argon	0.29	0.36	0.63	N, NC, SC, S	
Insulating LoE ² -272 Glass - Argon, GBG	0.29	0.33	0.57	N, NC, SC, S	
Insulating LoE ³ - 366 Glass - Argon	0.28	0.24	0.57	N, NC, SC, S	X
Insulating LoE ³ - 366 Glass - Argon, GBG	0.28	0.22	0.51	N, NC, SC, S	X

All Ultrex Sliding Patio Door - 3 mm glass					
Insulating LoE ² -272 Glass - Argon	0.31	0.34	0.58	N, NC, SC, S	
Insulating LoE ² -272 Glass - Argon, GBG	0.31	0.30	0.51	N, NC, SC, S	
Insulating LoE ³ - 366 Glass - Argon	0.30	0.20	0.52	N, NC, SC, S	X
Insulating LoE ³ - 366 Glass - Argon, GBG	0.30	0.20	0.45	N, NC, SC, S	X

Thermal and solar values are subject to update. Values are generated in accordance with NFRC 100-2004 and other applicable NFRC procedures. Argon gas is not available for the altitudes that require capillary tubes. Values are for select glazing options, for those options not listed please contact your local Integrity retailer.

